

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08K 5/523	A1	(11) International Publication Number: WO 96/11977 (43) International Publication Date: 25 April 1996 (25.04.96)
(21) International Application Number: PCT/US95/12801 (22) International Filing Date: 12 October 1995 (12.10.95) (30) Priority Data: 08/322,883 13 October 1994 (13.10.94) US (71) Applicant: AKZO NOBEL N.V. [NL/NL]; Velperweg 76, P.O. Box 9300, NL-6800 SB Arnhem (NL). (71)(72) Applicants and Inventors: MOY, Paul, Y. [US/US]; 10 Sandi Lane, Fishkill, NY 12524 (US). BRIGHT, Danielle, A. [US/US]; 21 Zabela Drive, New City, NY 10956 (US). (74) Agent: FENNELLY, Richard, P.; Akzo Nobel Inc., 7 Livingstone Avenue, Dobbs Ferry, NY 10522 (US).		(81) Designated States: CA, CN, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: POLYCARBONATE-CONTAINING POLYMERS FLAME RETARDED WITH OLIGOMERIC PHOSPHATE ESTERS (57) Abstract Polycarbonate-containing compositions are flame retarded with a mixture which comprises an arylene-bridged oligomeric polyphosphate ester and an effective amount of an alkylene-bridged diphosphate compound for increased flame retardancy efficacy and improved processing characteristics.		

FOR THE PURPOSES OF INFORMATION ONLY


Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

POLYCARBONATE-CONTAINING POLYMERS
FLAME RETARDED WITH OLIGOMERIC PHOSPHATE ESTERS

Background of the Invention

U.S. Patent No. 5,204,394 to J.C. Gosens et al. advocates the use of arylene-bridged oligomeric polyphosphate esters in the flame retarding of polycarbonate-containing polymer compositions. An oligomeric phosphate or blend of oligomeric phosphates are disclosed by the Gosens et al. patent as having the formula



where R_1 , R_2 , R_3 , and R_4 each represent an aryl or an alkaryl group chosen independently of each other and wherein X is an arylene group, m_1 , m_2 , m_3 , and m_4 , each independently of each other are 0 or 1 and wherein $n=1, 2, 3, 4$, or 5 or wherein, in the case of a blend of phosphates, n has an average value between 1 and 5.


Summary of the Invention

It has now been found that a mixture of an alkylene-bridged diphosphate compound and the foregoing type of arylene-bridged oligomeric polyphosphate ester is an effective flame retardant agent in the aforementioned types of polycarbonate-containing polymer compositions. It has been found that there is increased flame retardancy efficacy and improved processing characteristics for the mixture in such polymers.

Description of Preferred Embodiments

The polycarbonate-containing resins and the arylene-bridged oligomeric phosphate esters to which the present invention is applicable are described in the aforementioned U.S. Patent No. 5, 204,394 which is incorporated herein by reference in regard to such teaching.

The terminology "alkylene-bridged diphosphate compound" as used herein is to be understood to encompass monomeric and low oligomeric species of the formula



Where R is aryl, such as unsubstituted phenyl, n is a number ranging from 0 to about 5, and R¹ is alkylene of from 1 to 8 carbon atoms.

The present invention contemplates using a mixture comprising the arylene-bridged phosphate compositions and the alkylene-bridged compounds in a ratio of from about 1:2 to about 2:1 on a weight basis in the polycarbonate-containing compositions. Generally speaking, the amount of such mixture used in the polycarbonate-containing compositions will vary from about 1 % to about 25 % on the weight of the polycarbonate-containing composition.

The present invention is illustrated by the Examples which follow.

EXAMPLES 1-5

These Examples set forth cone calorimetric data (35.0 kW/m² irradiance) on neat PC/ABS, neat resorcinol diphosphate (RDP) and blends of RDP and neopentylglycol diphosphate at various weight amounts.

The polymers composites were preblended to a five to one (PC/ABS) ratio and extruded in a twin screw extruder to a homogeneous blend. The phosphate flame retardant mixtures ("FR" in the Table given below) were preblended in the prescribed ratios before addition to the composites. The incorporation of the flame retardants was accomplished by metering the liquid components into the melt stream of the extruder through a side port injector. All flame retardant composites are formulated to contain a small amount of powdered TEFLON fluoropolymer antidrip agent.

TABLE 1

			Peak Heat	Total Heat	Effective Heat
			Release		of Combustion
	<u>FR USED</u>	<u>%P</u>	<u>(kW/m²)</u>	<u>(KJ)</u>	<u>(MJ/kg)</u>
	NONE	-	201	32.12	3.48
	RDP (Neat)	0.91	69	17.79	2.04
	RDP/NPGDP (2/1)	0.92	62	18.83	2.02
	RDP/NPGDP (1/1)	0.71	52	14.66	1.61
	RDP/NPGDP (1/2)	0.80	43	16.04	1.85

EXAMPLES 6-10

These Examples show the melt flow viscosity data (ASTM-1238, Condition "I", 230°C, 3.8 kg) for the blends tested in each of Examples 1-5, above.

FR Sample (from Ex. 1-5) g/10 minutes


10	NONE	13.0
	RDP (Neat)	16.9
	RDP/NPGDP (2/1)	18.8
	RDP/NPGDP (1/1)	15.3
	RDP/NPGDP (1/2)	17.3

The foregoing data is presented for purposes of illustrating certain embodiments of the present invention and, for that reason, should not be construed in a limiting sense. The scope of protection sought is set forth in the claims which follow.

We Claim:


1. A flame retarded polycarbonate-containing composition which comprises a mixture comprising (1) an arylene-bridged oligomeric polyphosphate ester and (2) an effective amount of an alkylene-bridged diphosphate compound for increased flame retardancy efficacy and improved processing characteristics.

2. A composition as claimed in Claim 1 wherein the alkylene-bridged diphosphate compound is of the formula



wherein R is aryl, n is a number ranging from 0 to about 5, and R¹ is alkylene of from 1 to 8 carbon atoms.

3. A composition as claimed in Claim 1 wherein the alkylene-bridged diphosphate compound is of the formula



where R is unsubstituted phenyl, n is a number ranging from 0 to about 5, and R¹ is alkylene of from 1 to 8 carbon atoms and the arylene-bridged ester and the alkylene-bridged compound are in a ratio of from about 1:2 to about 2:1 on a weight basis.

4. A composition as claimed in Claim 1 wherein the amount of such mixture used in the polycarbonate-containing compositions will vary from about 1 % to about 25 % on the weight of the polycarbonate-containing composition.

5. A composition as claimed in Claim 2 wherein the amount of such mixture used in the polycarbonate-containing compositions will vary from about 1 % to about 25 % on the weight of the polycarbonate-containing composition.

6. A composition as claimed in Claim 3 wherein the amount of such mixture used in the polycarbonate-containing compositions will vary from about 1 % to about 25 % on the weight of the polycarbonate-containing composition.

7. A composition as claimed in Claim 1 wherein the arylene-bridged oligomeric polyphosphate ester is resorcinol diphosphate and the alkylene-bridged diphosphate compound is neopentylglycol diphosphate.

8. A composition as claimed in Claim 3 wherein the arylene-bridged oligomeric polyphosphate ester is resorcinol diphosphate and the alkylene-bridged diphosphate compound is neopentylglycol diphosphate.

9. A composition as claimed in Claim 5 wherein the arylene-bridged oligomeric polyphosphate ester is resorcinol diphosphate and the alkylene-bridged diphosphate compound is neopentylglycol diphosphate.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US95/12801

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : C08K 5/523

US CL : 524/127

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 524/127

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US, A, 5,204,394 (GOSENS ET AL.) 20 April 1993, see column 2, lines 5-41.	1-9
Y	US, A, 3,869,526 (COMBEY ET AL.) 04 March 1975, see column 1, lines 1-29 and column 3, lines 29-50.	1-9
Y	JP, A, 59-202,240 (DAIHACHI KAGAKU KOG KK) 16 November 1984, see the abstract	1-9
Y	JP, A, 59-45,351 (ADEKA-ARGUS CHEM KK) 14 March 1984, see the abstract.	1-9



Further documents are listed in the continuation of Box C.



See patent family annex.

*

Special categories of cited documents:

T

later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

A

document defining the general state of the art which is not considered to be of particular relevance

X

document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

E

earlier document published on or after the international filing date

Y

document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

L

document which may throw doubt on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

()

document referring to an oral disclosure, use, exhibition or other means

P

document published prior to the international filing date but later than the priority date claimed

&

document member of the same patent family

Date of the actual completion of the international search

Date of mailing of the international search report

31 JANUARY 1996

01 FEB 1996

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Authorized officer

VERONICA HOKE

Facsimile No. (703) 305-3230

Telephone No. (703) 308-2351

1